

AA-SERIES Slurry Spray Piping



Specifications

Erosion and Corrosion Resistant Pipe Systems

Pressure Rating: 100 psi*

Temperature Range: -40°F (-40°C) to 180°F (82°C)

Maximum Test Pressure: 1.5 x Rating

Complies with ASTM D5421 and ASTM D6041

Pipe and Fittings

a. Manufacturing Process


- Combination of contact molding and filament winding

b. Resin

- INEOS DERAKANE 411™ (Bisphenol A Epoxy Vinyl Ester)

c. Reinforcement

- Surfacing Veil: Polyester (Nexus) or 'C' Veil
- Glass: 'ECR' Glass



d. Construction

- All pipe and fittings have a 100 mil thick, erosion/corrosion, interior & exterior barrier comprised of one layer of veil (chemical barrier) and two layers of chopped strand glass (anti-wicking barrier) in a specially formulated erosion resistant resin matrix.

e. Curing

- Minimum Barcol hardness of 90% of resin manufacturer's specified value.

f. Flanges

- Flanges shall be full face FRP style. Drilling shall be in accordance with ANSI B16.5 Class 150. Flanges shall have a liner of the same construction as pipe and fittings and be qualified in accordance with ASTM D5421.

* Spray headers can be custom-designed to system requirements

™ Trademark, INEOS Composites or its subsidiaries, registered in various countries.

Specifications

g. Joints

o Pipe

Joints are matching tapered adhesive or butt type, and designed to provide equivalent strength to the pipe being joined.

o Branches

All branch connections and outlets have a molded internal radius.

o Spray Nozzles

Spray nozzles are joined to pipe by proven means of attachment, i.e. flanged, bonded, or mechanical joint.

h. Sizes

AA-series pipe is available in sizes 1" - 60" diameter.

i. Quality Assurance

All pipe and fittings manufactured under a formal QA program based on Quality Assurance Standard ISO 9001:2015.



RPS Composites Inc.

8375 Zeigler Blvd.

Mobile, AL 36689

Tel: (251) 445-4411

Fax: (251) 633-3318

Sales@RPSComposites.com

RPSComposites.com